



## ACRYLIC RESURFACER 620 AR (BLACK)

**DESCRIPTION** COLOR COURT ACRYLIC RESURFACER is made with 100% acrylic resins, bonding agents, sand, and other additives. It is used to fill, seal, and prepare asphalt surfaces prior to coating with the COLOR COURT Color System.

**USES** Use ACRYLIC RESURFACER to: (1) Seal rough and porous asphalt. (2) Fill in “birdbaths” or low areas. (3) Serve as a primer for bonding to old weathered asphalt. (4) Add years of protection to any asphalt playing area.

<b>MIXING</b>	<b>STANDARD</b>	<b>FILLER MIX</b>
Acrylic Resurfacer	55 Gallons	2-3 Parts
Water	20-30 Gallons	1 Part
Sand	150-250 LBS.	8-10LBS/GAL
Portland Cement	(Optional)	1-2 LBS/GAL

**APPLICATION** Apply with soft rubber squeegees. Apply when temperature is above 55 degrees F and when no temperatures below 40 degrees F are expected for at least 24 hours. Do not apply when rain is expected within 8 hours.

### **COVERAGE**

First Coat: 100-150 Sq. Ft. per Gal. (undiluted material)  
Second Coat: 125-175 Sq. Ft. per (Undiluted material)

**COLOR** Black or Neutral

### **DRYING TIME**

To touch: Less than 1 hour under normal conditions.  
To recoat: 4-8 hours under normal conditions.  
To topcoat: 12-24 hours.

**CLEAN UP** Water

**PACKAGING** 53-gallon drums and 5 gallon plastic pails.

**CAUTION** Do not allow to freeze.

### Physical Data

<b>Generic Type</b>	<b>Acrylic</b>
<b>Weight Per Gallon</b>	<b>9.3-9.5 lbs.</b>
<b>Viscosity (KU)</b>	<b>120-130 KU</b>
<b>Weight Solids</b>	<b>38 Percent</b>
<b>Volume Solids</b>	<b>31 Percent</b>
<b>MSFG</b>	<b>480</b>
<b>Boiling Point (F)</b>	<b>212</b>
<b>Type of Cure</b>	<b>Oxidation</b>
<b>Clean up Solvent</b>	<b>Water</b>
<b>HMIS Rating</b>	<b>H=1 R=0 F=0</b>

DISCLAIMER: To the best of our knowledge, the technical data contained herein are true and accurate on the date of issuance, But are subject to change without prior notice. This is not a specification, and all information is given in good faith. Since Conditions of use are beyond manufacturer’s control, information contained herein is without warranty, implied or otherwise, And final determination of the suitability of any information or material for the use contemplated, the manner of use, and whether There is any infringements of patents is the sole responsibility of the user. Manufacturer does not assume liability in connection With the use of the product relative to coverage, performance, or injury. For application in special conditions, consult the Manufacturer for detailed recommendations.