



Tinted Crack Patch Ready To Use 621cp

Description A colorful and functional world-class Crack filler system in a ready-to-use form for asphalt and concrete recreational sports use surfaces. Made with 100% acrylic latex Resins, high quality fibers and low mesh sand For optimal crack filling and reduced shrinkage.

USES New or weathered Tennis Courts, Running Tracks, Basketball, Volleyball, Paddle Courts, Swimming Pool Decks, Playground Structures, Patios, Pathways or other recreation and sports use Areas.

Features Custom blended for excellent crack filling properties.

Mixing Comes in a ready-to-use mix just agitate And fill.

Application Specifically formulated and manufactured for easy application by non-specialized personnel using conventional hand tools.

Coverage Average total application will vary depending on the depth of cracks. Actual coverage will also depend on the porosity and users methods of application

Colors Light Green. Other colors available upon request with a minimum batch size required.

Drying Time Dry to touch in 30 minutes. Recoat in as little as an hour. (Times based on 70°F ambient temperature and 50% relative humidity.)

Clean Up Use clean fresh water. All application tools should be cleaned immediately after use.

Packaging Available In 1 gallon cans, 5 gallon pails and 53 gallon drums

Cautions Store indoors and PROTECT FROM FREEZING! Apply only when temperature is at least 55 degrees F during and 12 hours following application. Do not apply if rain is imminen

Physical Data

Generic Type	Acrylic
Weight per gallon	14.8 lbs.
Volume Solids	70%
Weight Solids	76%
MSFG	365
Boiling Point (F)	212°F
Type Of Cure	Oxidation
Clean Up Solvent	Water
HMIS Rating	H=1
	R=0
	F=0

Disclaimer: To the best of our knowledge, the technical data contained herein are true and accurate on the date of issuance, but are subject to change without prior notice. This is not a specification, and all information is given in good faith. Since conditions of use are beyond manufacture's control, information contained herein is without warranty, implied or otherwise, and final determination of the suitability of any information or material for the use of contemplated, the manner of use, and whether there is any infringement of patents is the sole responsibility of the user. Manufacturer does not assume any liability in connection with the use of the product relative to coverage, performance, or injury. For application in special conditions, consult the manufacturer for detailed recommendations.