



## COLOR COURT SYSTEMS INC. DEEP PATCH BINDER

**DESCRIPTION** COLOR COURT ACRYLIC  
Deep Patch Binder is made with 100% acrylic resins,  
And bonding Agents It is used to fill, seal and prepare  
Asphalt and Concrete cracked surfaces prior to  
Coating with the COLOR COURT Color System.

**USES** Use Deep Patch Binder to: (1) Seal  
deep cracks (2) Fill in “birdbaths” or  
low areas. (3) Serve as a primer for bonding to old  
Asphalt and concrete surfaces. (4)

<b>MIXING</b>	<b>STANDARD</b>
Acrylic Binder	1 Part
Sand	5 Parts 80-100 Mesh
Portland Cement	1 Part

**APPLICATION** Apply with conventional trials.  
Apply when temperature is a minimum of 60 degrees  
F, and no temperature below 40 degrees F is  
Expected for at least 24 hours. Do not apply when  
Rain is expected within 8 hours.

### Physical Data

<b>Generic Type</b>	<b>Acrylic</b>
<b>Weight Per Gallon</b>	<b>8.65 – 8.95</b>
<b>Viscosity (KU)</b>	<b>90- 95 KU</b>
<b>Weight Solids</b>	<b>54 Percent</b>
<b>Volume Solids</b>	<b>49 Percent</b>
<b>MSFG</b>	<b>480</b>
<b>Boiling Point (F)</b>	<b>212</b>
<b>Type of Cure</b>	<b>Oxidation</b>
<b>Clean up Solvent</b>	<b>Water</b>
<b>HMIS Rating</b>	<b>H=1 R=0 F=0</b>

**COVERAGE**  
Will depend on the porosity or depth  
of the cracked surface.

**COLOR** White Transparent

**DRYING TIME**  
To touch: Less than 2 hour under  
normal conditions.  
to recoat: 4-8 hours under normal  
conditions.  
To topcoat: 12-24 hours.

**CLEAN UP** Clean water

**PACKAGING** 55-gallon drums  
And 5-gallon plastic pails.

**CAUTION** Do not allow to freeze.

DISCLAIMER: To the best of our knowledge, the technical data contained herein are true and accurate on the date of issuance, But are subject to change without prior notice. This is not a specification, and all information is given in good faith. Since Conditions of use are beyond manufacturer’s control; information contained herein is without warranty, implied or otherwise, And final determination of the suitability of any information or material for the use contemplated, the manner of use, and whether There is any infringements of patents is the sole responsibility of the user. Manufacturer does not assume liability in connection With the use of the product relative to coverage, performance, or injury. For application in special conditions, consult the Manufacturer for detailed recommendations.