



Customer Guidelines For Resurfacing Your Tennis Court

Scope Of Work:

This contract will include all labor, materials, and equipment necessary for the resurfacing of your tennis courts.

Surface Preparation:

The entire surface shall be thoroughly cleaned to remove dirt, grease, oil or other debris. Loose or peeling surface material shall be scraped and removed following the cleaning. Low areas shall be marked and filled if necessary. A low area is any area deep enough to hold sufficient water to cover a U.S nickel. These areas shall be leveled with **Color Courts Acrylic Resurfacer** or **Color Courts Crack Patch Mix**.

Color Coating:

The contractor shall apply two coats of Color Courts Acrylic Resurfacer to the inbounds and out of bounds areas the product will be mixed according to Color Courts Specifications. The application rate based on none diluted product.

The contractor shall apply a minimum or two (Three is Color Courts Recommendation) of Color Courts Filler/Finish. The colors for each area shall be pre-mixed by Color Court To provide customer with the best uniform and texture possible. The application rate on the first coat should be at least 100-150 sq. ft per gallon. The application rate for the second and third coats should be at least 150-200 sq. ft per gallon.

Line Marking:

Lines shall be laid out in accordance with the United States Tennis Association specifications. We will apply Color Courts Clear Acrylic (fuzz buster), then apply two coats of **Color Courts White Line Paint**.

References:

Tennis Court Contractor will provide customer with all the references needed to satisfy customers concerns. All work is handled in a professional manner. All containers and debris shall be removed when the job is completed.